

FIBERCON® SLAB Master Performance DATA SHEET

FIBERCON
SLAB MASTER™

Steel Fiber Reinforcement for Concrete



CAR 25 CDM ASTM A820 TYPE II

SPECIFICATIONS

Fiber Type:	Low carbon cut sheet steel fiber
Product Line:	Slab Master™
Product ID:	CAR 25 CDM (carbon, 25mm long, Cont. Deformed Mild)
Length:	1 Inch (25mm)
Dimensions:	Fibers are manufactured with tolerances set forth in ASTM A820
Aspect Ratio:	43
Tensile Strength	50,000 psi minimum per ASTM A820
Specific Gravity:	7.86
Melting Point:	2760° F
Specification:	The steel fiber specified shall be manufactured from a low carbon steel and meet physical property requirements of ASTM A820 Type II steel fiber. Fiber length shall be 25mm. The fibers shall be continuously deformed with an aspect ratio of 43. The steel fibers must be clean and free from rust, oil and deleterious material. The source should be in compliance under an ISO 9001 standard quality plan.

Fibercon International
100 South Third St.
Evans City, PA 16033
1-800-521-9908
1-724-538-5006 (tel)
1-724-538-9118 (fax)
fiberconfiber.com



FIRST IN FIBER

Fibercon UK, LTD.
Loughborough Technology Center
Unite 23-24 Epinal Way
Loughborough LE11 3GE, UK
44-1509-211860